

 \Rightarrow UL listed and can be labeled upon request in the following sizes .. 1 $\frac{1}{2}$ " (38mm), 1 $\frac{3}{4}$ " (45mm), 2 $\frac{1}{2}$ " (64mm) and 3" (74mm)

- >> Optional Mertex Wayout® couplings
- >> Available with the Identify® recessed area for color coding, bar coding and/or identification markings
- See table for available sizes
- >> Maintenance free; just wiped down and return to service
- » Constructed from specially formulated synthetic nitrile rubber to produce excellent abrasion resistance
- Highly resistant to fuels, chemicals, oils, heat & environmental pollutants. Impervious to molds, mildew & other airborne organisms
- >> All sizes and colors are tested according to the procedures specified in "2020 UL 19 radiant heat test"
- Carries a Five (5) Year Warranty
- With Mertex Wayout® technology couplings, Hydratak™ carries a 2-10-L warranty ("2 year All Hazards", "10 year against manufacturing defects" and "Lifetime against delamination")

orange	1.75in/45mm					
red	All sizes					
blue	1.75in/45mm					
green	1.75in/45mm					
yellow	All sizes (except 1.0in/38mm)					
Colors only availab	le in sizes as indicated					

Trade Bowl Size Size			Weight UN-COUPLED (50° / 15.2m)		COIL DIAMETER (50' / 15.2m)		Service Pressure		Proof Pressure		Burst Pressure			
1	ln.	mm	ln.	mm	Lbs	Kg	ln.	Cm.	PSI	kPa	PSI	kPa	PSI	kPa
ſ		25	1 9/32	33	9.3	4.2	16.0	40.6	300	2 070	600	4 140	900	6 200
	11/2	38	1 3/4	45	14.5	6.6	16.0	40.6	300	2 070	600	4 140	900	6 200
1	1 3/4	45	2	51	17.0	7.7	16.5	41.9	300	2 070	600	4 140	900	6 200
1	2	51	2 3/16	56	18.3	8.3	17.0	43.2	300	2 070	600	4 140	900	6 200
1	21/2	64	2 3/4	70	24.0	10.9	17.5	44.5	300	2 070	600	4 140	900	6 200
	3	76	3 5/16	84	29.0	13.2	18.0	18.0	300	2 070	600	4 140	900	6 200



HOW TO SPECIFY

HYDRATAK600™

THE HOSE SHALL BE SYNTHETIC RUBBER HOSE WITH MINIMUM SERVICE TEST PRESSURES AS DETAILED IN THE TABLE ON THE PREVIOUS PAGE

HOSE CONSTRUCTION

Hose shall be constructed of top quality synthetic yarns woven into an optimized web and then encased in a matrix of scientifically designed nitrile rubber. The resultant hose shall have excellent strength, low temperature flexibility, abrasion, oil and chemical resistance and low friction loss.

HOSE PHYSICAL PROPERTIES

Hose shall exceed all of the requirements of the latest NFPA 1961 Standard for Rubber Municipal Attack hoses. Underwriters Laboratories listing shall be available where applicable. Hose shall be flexible down to -35° F (-36° C) and be resistant to environmental pollutants. Hose shall be Ozone Resistant. Hose shall be Abrasion Resistant. When tested using the procedure listed in ASTM D2215, the hose reinforcement shall not show signs of damage after 15,000 cycles. Hose shall resist water absorption. When tested using the procedure listed in MIL STD 24606, water absorption shall be less than 1.0 lbs (0.45 Kg) per 100 feet (30.5 M).

WEIGHT, FLOW CHARACTERISTICS, SERVICE, TEST AND BURST PRESSURES

These shall be as detailed in the table on the previous page.

COUPLING SPECIFICATION

The female coupling shall have at least 3 reflective arrows (2 reflective arrows on 1.0" / 25mm size), in order to be visible from any position. The reflective arrows must be engraved into and below the surface of the coupling, to resist abrasion. The arrows must point in the direction of the water source for a standard hose connection.

The male coupling and female swivel nut must both have a recessed area to facilitate color and bar coding and/or identification markings.

TESTING

The hose must also be tested in accordance with the procedures specified in "2020 UL 19 radiant heat test"

STANDARDS

Must be UL listed and labeled upon request in the following sizes .. 1 $\frac{1}{2}$ " (38mm), 1 $\frac{3}{4}$ " (45mm), 2 $\frac{1}{2}$ " (64mm) and 3" (74mm).

WARRANTY

Hose assemblies, when supplied with couplings as specified above, shall have a "2 year All Hazards", "10 year against manufacturing defects" and "Lifetime against delamination" warranty.

Returns under this warranty shall be controlled by an RGO # system. Repair or replacement of hose is at the sole discretion of the Manufacturer.